

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
25 March 2004 (25.03.2004)

PCT

(10) International Publication Number
WO 2004/024994 A1

- (51) International Patent Classification⁷: **C25C 3/08**, 3/12, 7/00, 7/02
- (21) International Application Number: PCT/IB2003/003978
- (22) International Filing Date: 9 September 2003 (09.09.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: PCT/IB02/03759
11 September 2002 (11.09.2002) IB
- (71) Applicant: **MOLTECH INVENT S.A.** [LU/LU]; 6, rue Adolphe Fischer, L-1520 Luxembourg (LU).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **NGUYEN, Thinh**, T. [CH/CH]; Rte du Grand-Lancy 165b, CH-1213 Onex (CH). **DE NORA, Vittorio** [IT/BS]; Sandrigham House, Nassau (BS).
- (74) Agent: **CRONIN, Brian**; **MOLTECH S.A.**, Quai du Mont-Blanc 21, CH-1201 Geneva (CH).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declaration under Rule 4.17:

— of inventorship (Rule 4.17(iv)) for US only

Published:

— with international search report
— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **PROTECTION OF NON-CARBON ANODES AND OTHER OXIDATION RESISTANT COMPONENTS WITH IRON OXIDE-CONTAINING COATINGS**

(57) **Abstract:** A method of forming a dense and crack-free hematite-containing protective layer on a metal-based substrate for use in a high temperature oxidising and/or corrosive environment comprises applying onto the substrate a particle mixture consisting of: 60 to 99.95 weight%, in particular 70 to 95 weight% such as 75 to 85 weight%, of hematite with or without iron metal and/or ferrous oxide; 1 to 25 weight%, in particular 5 to 20 weight% such as 8 to 15 weight%, of nitride and/or carbide particles, such as boron nitride, aluminium nitride or zirconium carbide particles; and 0 to 15 weight%, in particular 5 to 15 weight%, of one or more further constituents that consist of at least one metal or metal oxide or a heat-convertible precursor thereof. The hematite particles are then sintered by heat treating the particle mixture to form the protective layer that is made of a microporous sintered hematite matrix in which the nitride and/or carbide particles are embedded and which contains, when present, said one or more further constituents. The mechanical, electrical and electrochemical properties of the protective layer can be improved by using an oxide of titanium, zinc, zirconium or copper. Typically, the protected substrate can be used in a cell for the electrowinning of a metal such as aluminium.